

CLAIMS

1. A semiconductor device comprising a MIS type field effect transistor, wherein the transistor comprising:
 - a silicon substrate;
 - a gate insulating film comprising a high-dielectric-constant
 - 5 metal oxide film and a silicon containing insulating film lying between the metal oxide film and the silicon substrate;
 - a silicon containing gate electrode formed on the gate insulating film; and
 - a sidewall including silicon oxide as a constituting material,
 - 10 which is formed on each lateral face side of the gate electrode; and
 - wherein a silicon nitride film is interposed between the sidewall and at least the lateral face of the gate electrode.
2. The semiconductor device comprising the MIS type field effect transistor according to Claim 1, wherein the silicon nitride film covers the lateral face of the high-dielectric-constant metal oxide film.
3. The semiconductor device according to Claim 1 or 2, wherein a silicon oxide film underlies the silicon nitride film.
4. A semiconductor device comprising a MIS type field effect transistor, wherein the transistor comprising:
 - a silicon substrate;
 - a gate insulating film comprising a high-dielectric-constant

8, wherein a silicon nitride film is laid between the high-dielectric-constant metal oxide film and the gate electrode.

10. The semiconductor device according to any one of Claims 1 to 9, wherein the high-dielectric-constant metal oxide film contains hafnium (Hf).

11. The semiconductor device according to any one of Claims 1 to 10, wherein a dielectric constant of the high-dielectric-constant metal oxide film is not less than 10.

12. The semiconductor device according to any one of Claims 1 to 3 and 8, wherein the high-dielectric-constant metal oxide film is absent beneath the sidewall.

13. The semiconductor device according to any one of Claims 1 to 12, wherein a gate length of the gate electrode is not greater than $1\ \mu\text{m}$.

14. A method of manufacturing a semiconductor device comprising the steps of:

forming a high-dielectric-constant metal oxide film over a silicon substrate after forming a silicon containing insulating film;

5 forming a film of a silicon containing gate electrode material over the high-dielectric-constant metal oxide film;

 forming a gate electrode by patterning the film of a gate electrode material;

 forming a pattern of the high-dielectric-constant metal oxide

- 5 metal oxide film and a silicon containing insulating film lying between the metal oxide film and the silicon substrate; and
- a silicon containing gate electrode formed on the gate insulating film; and
- wherein the high-dielectric-constant metal oxide film has a
- 10 nitrogen containing section at least on each of its lateral face sides.

5. The semiconductor device according to Claim 4, wherein the nitrogen-containing section is a silicon nitride film covering at least the lateral face of the high-dielectric-constant metal oxide film.

6. The semiconductor device according to Claim 5, wherein each lateral face of the gate insulating film has a recess with respect to the plane of the lateral face of the gate electrode, and, inside the recess, the silicon nitride film covers at least the lateral face of the high-dielectric-constant metal
- 5 oxide film.

7. The semiconductor device according to Claim 4, wherein the nitrogen containing section is formed by applying a nitriding treatment to each lateral face section of the high-dielectric-constant metal oxide film.

8. The semiconductor device according to any one of Claims 4 to 7, further comprising a sidewall including silicon oxide as a constituting material, which is formed on each lateral face side of the gate electrode.

9. The semiconductor device according to any one of Claims 1 to

10 film under the gate electrode by patterning the high-dielectric-constant metal oxide film;

forming a silicon nitride film over the entire surface;

forming a silicon oxide film on the silicon nitride film; and

etching back the silicon oxide film and the silicon nitride film

15 and thereby forming a sidewall on each lateral face of the gate electrode with the silicon nitride film lying therebetween.

15. The method of manufacturing a semiconductor device according to Claim 14, further comprising, after the step of forming the silicon nitride film, the step of applying etch back to the silicon nitride film so that the silicon nitride film lying on the gate electrode and the silicon substrate can be
5 removed, following which the silicon oxide film is formed over the entire surface and by etching back the silicon oxide film, a sidewall is formed on each lateral face of the gate electrode.

16. A method of manufacturing a semiconductor device comprising the steps of:

forming a high-dielectric-constant metal oxide film over a silicon substrate after forming a silicon containing insulating film;

5 forming a film of a silicon containing gate electrode material over the high-dielectric-constant metal oxide film;

forming a gate electrode by patterning the film of a gate electrode material;

forming a pattern of the high-dielectric-constant metal oxide
10 film and the silicon containing insulating film under the gate electrode by

patterning the high-dielectric-constant metal oxide film and the silicon containing insulating film;

forming a first silicon oxide film over the entire surface at a temperature of not higher than 600 °C;

15 forming a silicon nitride film on the first silicon oxide film;
 forming a second silicon oxide film on the silicon nitride film;
and

 etching back the second silicon oxide film, the silicon nitride
film and the first silicon oxide film and thereby forming a sidewall on each
20 lateral face of the gate electrode with the first silicon oxide film and the silicon
nitride film lying therebetween.

17. The method of manufacturing a semiconductor device
according to Claim 16, further comprising, after the step of forming the silicon
nitride film, the step of applying etch back to the silicon nitride film and the
first silicon oxide film so that the silicon nitride film and the silicon oxide film
5 lying on the gate electrode and the silicon substrate can be removed,
following which the second silicon oxide film is formed over the entire surface
and by etching back the second silicon oxide film, a sidewall is formed on
each lateral face of the gate electrode.

18. A method of manufacturing a semiconductor device comprising
the steps of:

 forming a high-dielectric-constant metal oxide film over a silicon
substrate after forming a silicon containing insulating film;

5 forming a film of a silicon containing gate electrode material

- over the high-dielectric-constant metal oxide film;
forming a gate electrode by patterning the film of a gate electrode material;
forming a pattern of the high-dielectric-constant metal oxide film under the gate electrode by patterning the high-dielectric-constant metal oxide film;
10 removing at least each lateral face section of the pattern of the high-dielectric-constant metal oxide film by means of isotropic etching to form a recess;
15 forming a silicon nitride film over the entire surface so as to fill up the recess;
etching the silicon nitride film in such a way that, inside the recess, at least the silicon nitride film covering each lateral face of the high-dielectric-constant metal oxide film can remain; and
20 forming a silicon oxide film over the entire surface and then etching back the silicon oxide film, and thereby forming a sidewall on each lateral face of the gate electrode.

19. A method of manufacturing a semiconductor device comprising the steps of:

- forming a high-dielectric-constant metal oxide film over a silicon substrate after forming a silicon containing insulating film;
5 forming a film of a silicon containing gate electrode material over the high-dielectric-constant metal oxide film;
forming a gate electrode by patterning the film of a gate electrode material;

forming a pattern of the high-dielectric-constant metal oxide
10 film under the gate electrode by patterning the high-dielectric-constant metal
oxide film;

applying a nitriding treatment to each lateral face section of the
pattern of the high-dielectric-constant metal oxide film; and

forming a silicon oxide film over the entire surface and then
15 etching back the silicon oxide film, and thereby forming a sidewall on each
lateral face of the gate electrode.

20. A method of manufacturing a semiconductor device comprising
the steps of:

forming a high-dielectric-constant metal oxide film over a silicon
substrate after forming a silicon containing insulating film;

5 forming a film of a silicon containing gate electrode material
over the high-dielectric-constant metal oxide film;

forming a gate electrode by patterning the film of a gate
electrode material;

forming a pattern of the high-dielectric-constant metal oxide
10 film under the gate electrode by patterning the high-dielectric-constant metal
oxide film;

forming a silicon oxide film over the entire surface at a
temperature of not higher than 600 °C; and

etching back the silicon oxide film, and thereby forming a
15 sidewall on each lateral face of the gate electrode.

21. The method of manufacturing a semiconductor device

according to any one of Claims 14, 15 and 18 to 20, wherein a pattern of the silicon containing insulating film is further formed under the gate electrode by patterning the silicon containing insulating film.

5

22. The method of manufacturing a semiconductor device according to any one of Claims 14 to 21, wherein the high-dielectric-constant metal oxide film contains hafnium (Hf).

23. The method of manufacturing a semiconductor device according to any one of Claims 14 to 22, wherein a dielectric constant of the high-dielectric-constant metal oxide film is not less than 10.

24. The method of manufacturing a semiconductor device according to any one of Claims 14 to 23, wherein a gate length of the gate electrode is not greater than 1 μ m.